

BIBLE PAPER

Technical Data Sheet

PRODUCT	GRADE / FINISH
BIBLE PAPER	Regular White / High Opacity / Cream / High White

TECHNICAL SPECIFICATIONS

GRADE	Nominal GSM	Basis Weight (g/m ²)	PPI (±30)	Opacity (%)	Tensile Strength MD (kN/m)	Whiteness (%)
Regular White	28	28 ± 1	1380	72 ± 2	≥1.4	87 ± 1.5
Regular White	30	30 ± 1	1320	73 ± 2	≥1.4	87 ± 1.5
Regular White	33	33 ± 1	1240	74 ± 2	≥1.5	87 ± 1.5
Regular White	35	35 ± 1	1180	75 ± 2	≥1.5	87 ± 1.5
Regular White	36	36 ± 1	1150	76 ± 2	≥1.5	87 ± 1.5
Regular White	38	38 ± 1	1100	77 ± 2	≥1.6	87 ± 1.5
Regular White	40	40 ± 1	1040	80 ± 2	≥1.6	87 ± 1.5
Regular White	45	45 ± 1	920	82 ± 2	≥1.7	87 ± 1.5
Regular White	50	50 ± 1	820	84 ± 2	≥1.8	87 ± 1.5
Regular White	60	60 ± 1.5	700	88 ± 2	≥1.8	87 ± 1.5
High Opacity	28	28 ± 1	1380	77 ± 2	≥1.4	88 ± 1.5
High Opacity	30	30 ± 1	1320	78 ± 2	≥1.4	88 ± 1.5
High Opacity	33	33 ± 1	1240	79 ± 2	≥1.5	88 ± 1.5
High Opacity	35	35 ± 1	1180	80 ± 2	≥1.5	88 ± 1.5
Cream	30	30 ± 1	1320	74 ± 2	≥1.4	75 ± 1.5
Cream	40	40 ± 1	1040	79 ± 2	≥1.6	75 ± 1.5
Cream	50	50 ± 1	820	84 ± 2	≥1.8	75 ± 1.5
High White	36	36 ± 1	1150	78 ± 2	≥1.5	92 ± 1.5
High White	40	40 ± 1	1040	80 ± 2	≥1.6	92 ± 1.5

The supplied source states that additional specifications may be produced to customer requirements.